

# OTTO Primer 1225

The highly viscous universal primer

Solvent-containing bonding agent combination

PR 1225

## Characteristics

- ▶ Primer to improve the adhesion on mineral, absorbent and some metallic substrates as well as some kinds of plastics
- ▶ Airing time at least 30 minutes (max. 3 hours)
- ▶ Film-forming
- ▶ Free of toluol

## Technical properties

Flash-off time at 23 °C/50 % RH [minutes] > 30 <sup>1</sup>

Consumption depending on the absorptivity of the substrate [g/m<sup>2</sup>] ~ 100 - 200

Density at + 23 °C [g/cm<sup>3</sup>] ~ 1,0

Shelf life at 23 °C/50 % RH [months] 9

1) Higher temperatures reduce the airing time, lower temperatures prolong it.

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

## Pretreatment

The adhesive surfaces must be cleaned and any contamination such as release agents, preservatives, grease, oil, dust, water, old adhesives/sealants and other substances impairing adhesion must be removed. Cleaning of non-porous substrates: Clean with OTTO Cleaner T (no flash-off time required) and a clean, lint-free cloth. Cleaning porous substrates: Clean surfaces mechanically, e.g. with a steel brush or a grinding disc, to remove loose particles.

## Important information

The primer has been developed for OTTO sealants / adhesives to ensure an optimal adhesion in combination with these. The interaction / compatibility to OTTO sealants / adhesives has been tested and released by our technical department. For others, and not mentioned above OTTO product groups, substrates or coatings we recommend preliminary tests.

Do not apply primer and cleanprimer beyond the joint edges and adhesion surfaces to avoid contaminants / optical changings.

## Application information

When applying primer on porous substrates (e. g. concrete), use a brush

When applying primer on non-porous substrates (such as metals and pvc), apply with a lint-free cotton cloth, not with a brush.

Apply primer thinly and evenly, excess primer forms a film, which affects the adhesive force

Drying time of at least 30 minutes necessary

The period of time between the application of the primer and the continuation of application may be extended to several hours, if dust accumulation is avoided.

Please be aware that no contaminated brush is immersed into the primer in order to avoid interferences with the primer.

Due to the many possible influences during and after application, the customer always has to carry out trials first.

Please observe the recommended shelf life which is printed on the packaging.



## Packaging

	100 ml aluminium bottle	1,000 ml aluminium bottle
<input type="radio"/> colourless	PR1225-50	PR1225-55
Pieces per packaging unit	15	5
Pieces per pallet		

## Safety precautions

Please observe the material safety data sheet.

## Disposal

Information about disposal: Please refer to the material safety data sheet.

## Warranty information

The above information and our technical application advice, whether verbal, in writing or by means of tests, are provided to the best of our knowledge, but are non-binding, including with regard to any third-party property rights. The information in this publication does not exempt the processor from carrying out their own tests on our products with regard to their suitability for the intended processes and purposes. The application, use and processing of our products and the products manufactured on the basis of our technical application advice are beyond our control and are therefore the sole responsibility of the processor. If the application for which our products are used is subject to an official authorisation requirement, the user is responsible for obtaining these authorisations. We reserve the right to adapt the product to technical progress and new developments. For the rest, we refer to our General Terms and Conditions, in particular with regard to any liability for defects. You can find our GTC at [www.otto-chemie.de](http://www.otto-chemie.de).