

OTTO StainEx

The natural stone degreasing paste



Special solvent-based paste

For indoor and outdoor application

STEX

Characteristics

- ▶ Ready-to-use paste
- ▶ Easy processing
- ▶ Successful usage may avoid expensive refurbishment of natural stone

Fields of application

- ▶ To remove grease from marble and natural stone where unsuitable sealants have caused migratory staining around the edges of the joints

Technical properties

Processing temperature from/to [°C] + 10 / + 25

Viscosity at 23 °C pasty

Density at 23 °C according to ISO 1183-1 [g/cm³] ~ 1,2

Consumption for approx. 500 cm² with a layer thickness of 5 mm [cartridges] 1

Shelf life at 23 °C/50 % RH for cartridge/foil bag [months] 12

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

Important information

Each natural stone is unique in its composition. For this reason it can not be excluded that even in case of an appropriate application of the degreasing paste a migratory staining may be intensified. This effect only appears exceptionally, it is mentioned here as a precaution.

Due to the multitude of natural stone species a preliminary test on a covered place is recommended. Hence guarantee cannot be given.

Do not apply OTTO StainEx if substrate temperatures are under + 5 °C or over + 20 °C.

Application information

OTTO StainEx eliminates migratory staining caused by unsuitable sealants and removes staining up to a depth of 2 cm. Please carry out a preliminary test to make sure, that the grease-stains can be removed with OTTO StainEx. This paste is only effective with grease-staining, other soilings on natural stones caused by primer, detergent or similar cannot be removed. Remove the sealant completely out of the joint. The joints should be dry when applying the paste. Put OTTO StainEx on the surface and spread it with a brush. Then apply OTTO StainEx again in order to achieve a layer thickness of at least 5 mm. After drying of the paste (at least 12 hours, paste has to be pulverised completely) sweep off the remaining solid parts with a broom or vacuum clean them. After cleaning no more dark stains should be visible. Remove remaining deeper stains by applying the paste a second or third time.

Clean the joints afterwards and seal them with the natural stone silicone OTTOSEAL® S 70.




Hermann Otto GmbH
 Krankenhausstr. 14 | 83413 Fridolfing, Germany
 ☎ +49 8684 908-0 | @ info@otto-chemie.de
 www.otto-chemie.com

💡 Application advice
 ☎ +49 8684 908-4300
 @ tae@otto-chemie.de

OTTO
 CHEMIE
 SEALING & BONDING

Due to the many possible influences during and after application, the customer always has to carry out trials first. Please observe the recommended shelf life which is printed on the packaging.

Packaging

310 ml cartridge	
 beige	STEX-20-C1378
Pieces per packaging unit	12
Pieces per pallet	1248

Safety precautions

Please observe the material safety data sheet.

Disposal

Information about disposal: Please refer to the material safety data sheet.

Warranty information

The above information and our technical application advice, whether verbal, in writing or by means of tests, are provided to the best of our knowledge, but are non-binding, including with regard to any third-party property rights. The information in this publication does not exempt the processor from carrying out their own tests on our products with regard to their suitability for the intended processes and purposes. The application, use and processing of our products and the products manufactured on the basis of our technical application advice are beyond our control and are therefore the sole responsibility of the processor. If the application for which our products are used is subject to an official authorisation requirement, the user is responsible for obtaining these authorisations. We reserve the right to adapt the product to technical progress and new developments. For the rest, we refer to our General Terms and Conditions, in particular with regard to any liability for defects. You can find our GTC at www.otto-chemie.de.