Technical datasheet

OTTOPUR OP 960 SPECIAL

The B1 dosing foam

1-component PU dosing foam | For indoor and outdoor application | OP 960

GEV-EMICODE EC 1 PLUS very low emission

Characteristics

- B1 – flame-resistance in accordance with DIN 4102 Part 1
- Supports the smoke-tight installation of safety doors
- 60 dB sound insulation according to EN ISO 717-1
- 0.036 W/mK insulation value according to DIN 52612
- Foam yield approx. 45 l per 750 ml can
- Can be cut after approx. 50 minutes
- Can be loaded after approx. 12 hours

Fields of application

- Window installation (for clean and controlled backfilling and insulating sealing of joints for windows and shutter casings)
- Filling of joints for door frames but not for mere assembly purposes without additional, mechanical fastening
- Foaming of small wall recesses, all types of cable passages and other cavities

Standards and tests

- General building supervisory test certificate in accordance with DIN 4102-1 B1
- EMICODE® EC 1 Plus - very low emission
- French VOC-emission class A+

Technical properties

Joint-foamed yield (EN 17333-1) [lm]	~ 28
Foam yield (EN 17333-1) [l]	~ 45
Temperature of can from/to [°C]	+ 5 / + 35 [1]
Ambient temperature [°C]	+ 5 / + 35 [1]
Temperature of substrate [°C]	+ 5 / + 35 [1]
Skin formation (EN 17333-3) [min]	~ 9
Cuttability (EN 17333-3) [min]	~ 50
Loadable, depending on the layer thickness [hours]	~ 12
Free-foaming density (EN 17333-1) [kg/m³]	~ 23
Evaluated joint sound reduction index joint width 10mm [dB]	≥ 60
Evaluated joint sound reduction index joint width 20mm [dB]	≥ 59
Thermal conductivity λ [W/mK]	~ 0,036
Compressive strength (EN 17333-4) [kPa]	~ 35
Tensile strength (EN 17333-4) [kPa]	~ 115
Tensile expansion (EN 17333-4) [%]	~ 12
Shear stability (EN 17333-4) [kPa]	~ 45

Hermann Otto GmbH
Krankenhausstr. 14 | 83413 Fridolfing, Germany
+49 8684 908-0 | @ info@otto-chemie.de
www.otto-chemie.com

Application advice
+49 8684 908-4300
@ tae@otto-chemie.de

OTTO CHEMIE SEALING & BONDING

Dimensional stability (EN17333-2) [%]	+- 5
Hardening pressure (EN 17333-2) [kPa]	~ 1,5
Post-expansion (EN 17333-2) [%]	~ 60
Temperature resistance from/to [°C]	- 40 / + 80 [2]
Shelf life at 23 °C/50 % RH [months]	12 [3]
Colour	pink

1) optimal processing temperature + 20 °C

2) temporarily + 100 °C

3) from date of manufacture, store unopened cans upright

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

Important information

A at least partly filled aerosol can should be mounted permanently to the dosing gun, so that the OTTOPUR foam in the gun stays under pressure. Please shut the adjusting screw after use.
Never remove the can by using force.
Do not clean the adapter with a solid object.
If the dosage gun has to be taken out of service, it must be cleaned using OTTOPUR Cleaner immediately following unscrewing. Regular use considerably extends the service life and functionality of the dosage guns.
Hardened foam residue can only be mechanically removed.
Fresh product residues can be removed with OTTOPUR Cleaner or OTTO Cleaning wipes. In case of skin contact, wash with water and soap and rinse thoroughly.
Please note: Can is under pressure. Protect from UV-radiation and temperatures over +50 °C.

Application information

1. Substrates and building materials have to be cleaned and well moistened. 2. Protect components from deformation by using a brace. 3. Shake the can thoroughly (at least) 20 times. Remove cap of can. 4. Screw the can into the adapter – Do not tighten it! 5. For initial operation press the trigger for approximately 10 seconds and let the material flow out completely (filling of channel with PUR-foam and removing of residual humidity). 6. The applicator gun is ready to use. For application hold aerosol can up-side-down and the applicator gun vertically. 7. Dispense the foam by adjusting the trigger and by adjusting the screw. 8. Before mounting a new can to the applicator gun, shake new can thoroughly and remove empty can immediately (within 1 minute maximum). 9. Replace the empty can by a new can quickly to avoid curing of the PUR-foam in the adapter. 10. Remove uncured foam from the adapter with OTTOPUR-Cleaner. 11. Remove foam residues from the nozzle with a piece of wood (or something similar).
Due to the many possible influences during and after application, the customer always has to carry out trials first.
Please observe the recommended shelf life which is printed on the packaging.

Packaging

	750 ml aerosol can
pink	OP960-85
Pieces per packaging unit	**12**
Pieces per pallet	**504**

Safety precautions

Please observe the material safety data sheet.

Disposal

-
Information about disposal: Please refer to the material safety data sheet.

Brand information

EMICODE® is a registered trademark of GEV e. V. (Düsseldorf, Germany)

Warranty information

The above information and our technical application advice, whether verbal, in writing or by means of tests, are provided to the best of our knowledge, but are non-binding, including with regard to any third-party property rights. The information in this publication does not exempt the processor from carrying out their own tests on our products with regard to their suitability for the intended processes and purposes. The application, use and processing of our products and the products manufactured on the basis of our technical application advice are beyond our control and are therefore the sole responsibility of the processor. If the application for which our products are used is subject to an official authorisation requirement, the user is responsible for obtaining these authorisations. We reserve the right to adapt the product to technical progress and new developments. For the rest, we refer to our General Terms and Conditions, in particular with regard to any liability for defects. You can find our GTC at www.otto-chemie.de.