

OTTOSEAL® A 210

The painters' acrylic



1-component acrylic sealant

For indoor and outdoor application

A 210

Characteristics

- ▶ 10% permissible movement capability as per ISO 9046 (manufacturer's test)
- ▶ Can be painted and varnished – please observe application instruction in Technical Data Sheet
- ▶ No yellowing/greying
- ▶ Compatible with coatings according to DIN 52452 - No interaction with existing and adjacent coatings
- ▶ Frost-resistant - Can be stored and transported in temperatures as low as -10 °C for up to 48 hours

Fields of application

- ▶ Sealing of connection joints in the base, wall and ceiling areas, such as on window sills and shutter casings

Standards and tests

- ▶ Tested according to EN 15651 – Part 1: F EXT-INT 7.5 P
- ▶ Tested fire behaviour in accordance with EN 13501: class E
- ▶ French VOC-emission class A+
- ▶ Suitable for applications according to IVD instruction sheet no. 12+20+29+31+32+35 (IVD = German industry association sealants)

Technical properties

Skin-forming time at 23 °C/50 % RH [minutes]	~ 15
Processing temperature from/to [°C]	+ 5 / + 35
Viscosity at 23 °C	pasty, stable
Density at 23 °C according to ISO 1183-1 [g/cm ³]	~ 1,6
Shore-A-hardness according to ISO 868	~ 12
Permissible movement capability [%] according to ISO 9046	10
Permissible movement capability [%] according to EN 15651 Part 1	7,5
Stress expansion modulus at 100 % according to ISO 37, type 3 [N/mm ²]	~ 0,35
Tensile expansion according to ISO 37, type 3 [%]	~ 200
Tensile strength according to ISO 37, type 3 [N/mm ²]	~ 0,4
Temperature resistance from/to [°C]	- 20 / + 80
Joint width [mm]	25
Shrinkage of volume according to ISO 10563 [%]	~ 20
Shelf life at 23 °C/50 % RH for cartridge/foil bag [months]	12 ^{1 2}

1) from production

2) Frost-free storage



Hermann Otto GmbH
 Krankenhausstr. 14 | 83413 Fridolfing, Germany
 ☎ +49 8684 908-0 | @ info@otto-chemie.de
 www.otto-chemie.com

Application advice
 ☎ +49 8684 908-4300
 @ tae@otto-chemie.de



SEALING & BONDING

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

Pretreatment

The adherent surfaces have to be clean, free from dust and grease as well as sustainable.

The adhesive surfaces must be cleaned and any contamination such as release agents, preservatives, grease, oil, dust, water, old adhesives/sealants and other substances impairing adhesion must be removed. Cleaning of non-porous substrates: Clean with OTTO Cleaner T (no flash-off time required) and a clean, lint-free cloth. Cleaning porous substrates: Clean surfaces mechanically, e.g. with a steel brush or a grinding disc, to remove loose particles.

Primer table

The demands on elastic sealings and bondings depend on the respective exterior influences. Extreme fluctuations in temperature, tensile or shear forces, repeated contact with water etc. demand high requirements of a bonding. In such cases it is advisable to apply primer according to the recommendations of our technical department (e. g. +/OTTO Primer 1216) in order to achieve a resilient bonding.

Acrylic bathroom surfaces (e. g. bath tubs)	-
Acrylic glass/PMMA	OTTOSEAL® S 72
Aluminium	+ / 1226
Aluminium anodized	+ / 1225
Concrete	+ / 1105 / 1225
Lead	-
Chrome	+ / 1225
Stainless steel	+ / 1225
Fibre cement	+ / 1105 / 1225
Gypsum plasterboard	+ / 1225
Glass	-
Wood, painted (solvent systems)	+ / 1226
Wood, painted (aqueous systems)	+ / 1226
Wood, varnished (solvent systems)	+ / 1226
Wood, varnished (aqueous systems)	+ / 1226
Wood, untreated	+ 1105 / 1225
Ceramic, glazed	+ / T
Ceramics, unglazed	+ / T
Plastic profiles (unplasticized, e. g. Vinnolit)	+ / 1105
Copper	+ / 1226
Melamine resin panels	-
Brass	+ / 1105
Natural stone / marble	OTTOSEAL® S 70
Polypropylene	-
Cellular concrete	+ / 1105 / 1225
Plaster	+ / 1105 / 1225
PVC unplasticized	+ / 1105
PVC-soft-foils	-
Tinplate	-
Zinc, galvanised iron	-

+ = good adherence without primer

- = not suitable

T = Test/pilot test advised

The table above is based on adhesive experiments under laboratory conditions. In real conditions, the adhesive properties depend on an array of external influences (weather, dirt, loads, etc.). For this reason, the adhesion table is for orientation purposes only and does not represent any binding information.

Important information

Before applying this product the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with it and also amongst each other and do not damage or alter (e. g. discolour) each other. As for the materials that will be used at a later stage in the surrounding area of the product the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the product. In case of doubt the user

should consult the respective manufacturer of the material.

Do not apply at temperatures below +5 °C.

Curing / drying leads to a colour change of the sealant. The final colour is attained after complete curing.

Compatibility with water-based paints is given in the majority of cases. Due to the variety of available paint systems, we recommend either to test the compatibility of sealant and paint or to contact our technical department.

When painting the sealant in joints with little movement, a drying time of at least one week has to be observed.

Avoid contact with materials which contain bitumen and which release solvents, e. g. butyl, EPDM, neoprene, insulating- and bituminous paint.

Application information

Apply the sealant evenly with hand operated- or air-compressed gun, surface must be pressed smoothly with moistened tools before skin forming begins. Remove uncured contaminants with water immediately.

Our product can be overcoated with paint or varnish. The compatibility between the coating and our product has to be checked before the application by the user/processor - possibly under production conditions. Our OTTO application technology will gladly support you non-committally. If, in exceptional cases, after successful compatibility test our product is coated over the entire surface, this coating must also be able to follow the elastic movement of the sealant. Otherwise crack formations in the coat of paint or optical impairments may occur.

Due to the many possible influences during and after application, the customer always has to carry out trials first.

Please observe the recommended shelf life which is printed on the packaging.

We recommend to store our products in unopened original packagings dry (< 60 % RH) at temperatures of +15 °C up to +25 °C. If the products are stored and / or transported at higher temperatures / air humidity for longer periods (some weeks), a diminution of durability or a change of material characteristics may arise.

Packaging

	300 ml cartridge	400 ml aluminium foil bag	580 ml aluminium foil bag
○ white	A210-03-C01	on request	A210-08-C01
Pieces per packaging unit	20	20	20
Pieces per pallet	1200	900	880

No special colours possible.

Due to typographical reasons the colours shown below may differ from the original colours of the products.

Safety precautions

Please observe the material safety data sheet.

After curing, the product is odourless.

Disposal

Information about disposal: Please refer to the material safety data sheet.

Warranty information

The above information and our technical application advice, whether verbal, in writing or by means of tests, are provided to the best of our knowledge, but are non-binding, including with regard to any third-party property rights. The information in this publication does not exempt the processor from carrying out their own tests on our products with regard to their suitability for the intended processes and purposes. The application, use and processing of our products and the products manufactured on the basis of our technical application advice are beyond our control and are therefore the sole responsibility of the processor. If the application for which our products are used is subject to an official authorisation requirement, the user is responsible for obtaining these authorisations. We reserve the right to adapt the product to technical progress and new developments. For the rest, we refer to our General Terms and Conditions, in particular with regard to any liability for defects. You can find our GTC at www.otto-chemie.de.