

# Novasil® S 44 SP 6212

The 2-component silicone adhesive and sealant for the domestic appliances industry

S 44 SP 6212

## Characteristics

- ▶ Neutral, condensation-curing 2-component silicone adhesive and sealant based on alkoxy
- ▶ Excellent adhesion without primer on glass ceramics as well as on coated and uncoated metals
- ▶ Fast curing even in thick layers
- ▶ Reduced cycle times - due to the fast curing bonded parts can be further processed extremely soon
- ▶ Excellent temperature resistance
- ▶ High adhesion strength
- ▶ Low odour
- ▶ Especially matched viscosity



## Fields of application

### Household appliances industry:

- ▶ Bonding and sealing of household appliances
- ▶ Bonding and sealing of glass ceramic hobs
- ▶ Bonding of angle brackets for oven panels, oven panes, door handles

## Standards and tests

- ▶ According to UL FLAME CLASSIFICATION 94 HB
- ▶ Novasil® S 44 SP 6212 / OTTOCURE S-CA 2175 complies with the requirements of the UL testing standard 746C "Standard for polymeric materials – use in electrical equipment evaluations", application temperature +130°C

## Technical properties

### Single components:

#### Component A

Colour	white
Viscosity at 23 °C	pasty
Density at 23 °C according to ISO 1183-1 [g/cm <sup>3</sup> ]	~ 1,31
Shelf life at 23 °C/50 % RH [months]	9 <sup>1</sup>

1) from production

### Hermann Otto GmbH

Krankenhausstr. 14 | 83413 Fridolfing, Germany  
☎ +49 8684 908-0 | @ info@otto-chemie.de  
www.otto-chemie.com

💡 Application advice  
☎ +49 8684 908-4300  
@ tae@otto-chemie.de



SEALING & BONDING

**Component B**  
**OTTOCURE**

	S-CA 2160	S-CA 2175	S-CA 2050	S-CA 2465
Colour	black	black	black	black
Viscosity at 23 °C	pasty	pasty	pasty	pasty
Density at 23 °C according to ISO 1183-1 [g/cm <sup>3</sup> ]	~ 1,24	~ 1,24	~ 1,24	~ 1,24
Shelf life at 23 °C/50 % RH [months] <sup>1</sup>	6	6	6	6

1) from production

**Mixed components**  
**With OTTOCURE**

	S-CA 2160	S-CA 2175	S-CA 2050	S-CA 2465
Colour	black	black	black	black
Viscosity at 23 °C	pasty	pasty	pasty	pasty
Pot life at 23 °C/ 50% RH [minutes]	1 - 5	5 - 10	8 - 15	10 - 15
Shore-A-hardness after 30 minutes	> 5	-	-	-
Shore-A-hardness after 1 hour	> 15	> 3	-	-
Shore-A-hardness after 2 hours	> 20	> 15	> 10	> 8
Shore-A-hardness after 24 hours	> 35	> 35	> 32	> 30

**Vulcanisate:**

	S-CA 2160	S-CA 2175	S-CA 2050	S-CA 2465
Density at 23 °C according to ISO 1183-1 [g/cm <sup>3</sup> ]	~ 1,3	~ 1,3	~ 1,3	~ 1,3
Shore-A-hardness according to ISO 868	~ 43 - 47	~ 43 - 47	~ 43 - 47	~ 35 - 40
Temperature resistance from/to [°C]	-40 / +200 <sup>1 2</sup>	-40 / +200 <sup>1 2</sup>	-40 / +200 <sup>1 2</sup>	-40 / +200 <sup>1 2</sup>
Tensile strength according to ISO 37, type 3 [N/mm <sup>2</sup> ]	~ 2,5	~ 2,5	~ 2,5	~ 2,5
Tensile expansion according to ISO 37, type 3 [%]	~ 375	~ 375	~ 375	~ 500
Stress expansion modulus at 100 % according to ISO 37, type 3 [N/mm <sup>2</sup> ]	~ 0,8	~ 0,8	~ 0,8	~ 0,7
Shrinkage of volume according to ISO 10563 [%]	~ 4	~ 4	~ 4	~ 4

1) up to 500 h

2) temporarily up to +250 °C

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications. The mechanical parameters given here are material characteristics and cannot be used as basis for dimensioning the bonding joint. To this end please contact our technical department.

## Pretreatment

The adhesive surfaces must be cleaned and any contamination such as release agents, preservatives, grease, oil, dust, water, old adhesives/sealants and other substances impairing adhesion must be removed.

The adherent surfaces have to be clean, free from fat, dry and sustainable.

The demands on elastic sealings and bondings depend on the respective exterior influences. Extreme fluctuations in temperature, tensile or shear forces, repeated contact with water etc. demand high requirements of a bonding. In such cases it is advisable to apply primer in order to achieve a resilient bonding. Please consult our technical department.

## Important information

Before applying this product the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with it and also amongst each other and do not damage or alter (e. g. discolour) each other. As for the materials that will be used at a later stage in the surrounding area of the product the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the product. In case of doubt the user should consult the respective manufacturer of the material.

Paints, lacquers, plastics and any other coatings must be compatible to the adhesive/sealant.

During curing small amounts of alcohol are released.

Ensure good ventilation during application and curing.

Constructional details of the adhesion must be agreed upon by our technical department.

## Application information

<b>Processing temperature from/to [°C]</b>	+10 / +25 <sup>1</sup>
<b>Mixing ratio according to weight (base A : curing agent B)</b>	10,6 : 1 <sup>2</sup>
<b>Mixing ratio according to volume (base A : curing agent B)</b>	10 : 1
<b>Maximum permissible deviation from the mixing ratio [%]</b>	± 10
<b>Recommended following plate pressure, component A [bar]</b>	2 - 3
<b>Recommended following plate pressure, component B [bar]</b>	< 1,5
<b>Maximum temperature during curing [°C]</b>	+60

1) temporarily up to + 30 °C

2) With Ottocure S-CA 2050: 10.5: 1

Avoid entrapment of air during mixing. Therefore we recommend to use a mixing equipment.

For seals in the mixing and dosing system that are in direct contact with the adhesive/sealant, we recommend using (plasticiser-free) EPDM seals or even more resistant FFKM seals. If other sealing materials are used, please consult our Application Technology department.

Component A does not react with air humidity and is stable under normal conditions (23 °C, 50 % RH).

Component B is sensitive to moisture and therefore must be protected from moisture.

In order to achieve good adhesion and good mechanical properties air entrapment must be avoided.

Due to the many possible influences during and after application, the customer always has to carry out trials first.

Please observe the recommended shelf life which is printed on the packaging.

We recommend to store our products in unopened original packagings dry (< 60 % RH) at temperatures of +15 °C up to +25 °C. If the products are stored and / or transported at higher temperatures / air humidity for longer periods (some weeks), a diminution of durability or a change of material characteristics may arise.

To make sure the mixing is correct the user has to carry out accompanying quality checks during application. The according necessary tests have to be gathered from the document "Accompanying Quality Checks for the processing of 2-component Silicones", which is available from our technical department.

## Packaging

Packagings and colours on request

## Safety precautions

Please observe the material safety data sheet.

After curing, the product is odourless.

## **Disposal**

Information about disposal: Please refer to the material safety data sheet.

## **Warranty information**

The above information and our technical application advice, whether verbal, in writing or by means of tests, are provided to the best of our knowledge, but are non-binding, including with regard to any third-party property rights. The information in this publication does not exempt the processor from carrying out their own tests on our products with regard to their suitability for the intended processes and purposes. The application, use and processing of our products and the products manufactured on the basis of our technical application advice are beyond our control and are therefore the sole responsibility of the processor. If the application for which our products are used is subject to an official authorisation requirement, the user is responsible for obtaining these authorisations. We reserve the right to adapt the product to technical progress and new developments. For the rest, we refer to our General Terms and Conditions, in particular with regard to any liability for defects. You can find our GTC at [www.otto-chemie.de](http://www.otto-chemie.de).