

Novasil® S 825

The low-viscosity 2-component silicone potting compound with a thermal conductivity of 0.5 W/mK

S 825

Characteristics

- ▶ 2-component silicone potting compound
- ▶ Based on a neutral, condensation curing system
- ▶ Cures at room temperature
- ▶ Releases alcohol as splitting product during curing.
- ▶ Non-corrosive
- ▶ Electrically non-conductive
- ▶ Fast curing
- ▶ Thermally conductive



Fields of application

- ▶ Potting of junction boxes in the PV-industry
- ▶ Potting and coating of electronic and electric components
- ▶ Waterproof sealing of measuring units
- ▶ Potting/coating of electrical circuit boards and housings

Standards and tests

- ▶ According to UL FLAME CLASSIFICATION 94 V-1

Technical properties

Single components:

Component A

Colour	C01 white
Viscosity (Brookfield, Sp.05, 10 UPM) [mPas]	~20000
Density at 23 °C according to ISO 1183-1 [g/cm³]	~ 1,4
Shelf life at 23 °C/50 % RH [months]	9 ¹

1) from production

Component B

OTTOCURE S-CA 2475

Colour	C00 transparent ¹
Viscosity (Brookfield, Sp.02, 100 UPM) [mPas]	~ 50
Density at 23 °C according to ISO 1183-1 [g/cm³]	~ 1,0
Shelf life at 23 °C/50 % RH [months]	9 ²

1) During storage, the material may discolour a yellowish or brownish colour, even in an unopened container. This is typical of the material and is not a product defect. The technical properties of the material remain unaffected within the guaranteed storage stability.

2) from production

Mixed components

with OTTOCURE S-CA 2475

Colour	white
Viscosity (Brookfield, Sp.05, 20 UPM) [mPas]	~ 20000

Hermann Otto GmbH

Krankenhausstr. 14 | 83413 Fridolfing, Germany
 ☎ +49 8684 908-0 | @ info@otto-chemie.de
 www.otto-chemie.com

💡 Application advice
 ☎ +49 8684 908-4300
 @ tae@otto-chemie.de



SEALING & BONDING

Density at 23 °C according to ISO 1183-1 [g/cm ³]	~ 1,4
Pot life at 23 °C/50 % RH [minutes]	~ 8
Shore-A-hardness after 4 hours	~ 40
Shore-A-hardness after 24 hours	~ 50

Vulcanisate:

Density at 23 °C according to ISO 1183-1 [g/cm ³]	~ 1,4
Shore-A-hardness according to ISO 868	~ 53
Temperature resistance from/to [°C]	- 40 / + 150 ¹
Tensile strength according to ISO 37, type 3 [N/mm ²]	~ 1,8
Tensile expansion according to ISO 37, type 3 [%]	~ 90
Thermal conductivity λ [W/mK]	~ 0,50
Volume resistance ρ according to DIN IEC 93 [Ω*cm]	~ 9,2*10 ¹²
Dielectric strength according to DIN IEC-243-2 [kV/mm]	~ 17

1) After complete curing a temperature resistance up to approx. +150 °C can be reached. Constant use under high temperatures and/or high humidity (RH > 60 %) may change the properties of the material or lead to an interaction with neighbouring materials.

These data are not suitable for the issue of specifications. Please contact OTTO-CHEMIE before issuing specifications.

Pretreatment

The adhesive surfaces must be cleaned and any contamination such as release agents, preservatives, grease, oil, dust, water, old adhesives/sealants and other substances impairing adhesion must be removed.

The adherent surfaces have to be clean, free from fat, dry and sustainable.

The demands on elastic sealings and bondings depend on the respective exterior influences. Extreme fluctuations in temperature, tensile or shear forces, repeated contact with water etc. demand high requirements of a bonding. In such cases it is advisable to apply primer in order to achieve a resilient bonding. Please consult our technical department.

Certain plastics need a special surface treatment to achieve optimal adhesion on it. Please contact our technical department for this.

Important information

Before applying this product the user has to ensure that the materials in the area of contact (solid, liquid and gaseous) are compatible with it and also amongst each other and do not damage or alter (e. g. discolour) each other. As for the materials that will be used at a later stage in the surrounding area of the product the user has to clarify beforehand that the substances of content or evaporations do not lead to an impairment or alteration (e. g. discolouration) of the product. In case of doubt the user should consult the respective manufacturer of the material.

During curing small amounts of alcohol are released.

Ensure good ventilation during application and curing.

Contact with chemicals and when used in light protected applications can lead to a slight yellowing of the cured product. A possible change in colour does not necessarily influence the functionality.

Application information

Processing temperature from/to [°C]	+10 / +25 ¹
Mixing ratio according to weight (base A : curing agent B)	14,3 : 1
Mixing ratio according to volume (base A : curing agent B)	10 : 1
Maximum permissible deviation from the mixing ratio [%]	± 10

1) temporarily up to + 30 °C

Avoid entrapment of air during mixing. Therefore we recommend to use a mixing equipment.

As the filling agents in component A can settle down (sedimentation) during storage, it must be stirred up homogeneously in the original packaging prior to mixing it with component B or prior to filling it into the storage containers of a mixing and dosing installation.

Component A does not react with air humidity and is stable under normal conditions (23 °C, 50 % RH).

Component B is sensitive to moisture and therefore must be protected from moisture.

Advice for the lay out design of the mixing and dosing installation: we advise the use of stainless steel storage containers and EPDM o-ring sealing. To prevent the diffusion of humidity please use hoses with Teflon coating inside. If you decide to use different sealing materials, please contact the Application Engineering department.

Please do not use any overpressure to transport component A and B from the storage containers into the mixing and dosing head to avoid air entrapments and bubbles in the mixed material. The storage container of component A must be equipped with a stirring device in order to avoid sedimentation.

Packaging

Packagings and colours on request

Safety precautions

Please observe the material safety data sheet.

Disposal

Information about disposal: Please refer to the material safety data sheet.

Warranty information

The above information and our technical application advice, whether verbal, in writing or by means of tests, are provided to the best of our knowledge, but are non-binding, including with regard to any third-party property rights. The information in this publication does not exempt the processor from carrying out their own tests on our products with regard to their suitability for the intended processes and purposes. The application, use and processing of our products and the products manufactured on the basis of our technical application advice are beyond our control and are therefore the sole responsibility of the processor. If the application for which our products are used is subject to an official authorisation requirement, the user is responsible for obtaining these authorisations. We reserve the right to adapt the product to technical progress and new developments. For the rest, we refer to our General Terms and Conditions, in particular with regard to any liability for defects. You can find our GTC at www.otto-chemie.de.